

NICKEL ALLOY

400 - 2.4360



400 - 2.4360

Nickel alloy 400 is a single phase, solid-solution nickel-copper alloy that offers superior resistance to many corrosive environments over temperatures ranging from sub-zero to 800°F. It is known for its resistance to corrosion, especially in environments where hydrofluoric acid and fluorine gases are present, and is only hardenable through cold working, rather than heat treatment.

KEY FEATURES

- Excellent corrosion resistance
- High ductility
- Good mechanical properties
- Thermal stability
- Non-magnetic

CHEMICAL PROPERTIES

Nickel (Ni)	Copper (Cu)	Iron (Fe)	Manganese (Mn)	Silicone (Si)	Carbon (C)	Sulphur (S)
63%	28-34%	2.5%	2%	0.5%	0.3%	0.03%

MECHANICAL PROPERTIES

Tensile strength (N/mm ²)	700
Yield strength (N/mm ²)	310
Elongation (% in 4D)	35
Hardness - Rockwell (HRB) max	80
Hardness - Brinell (HB) max	-

PHYSICAL PROPERTIES

Density (kg/m ³)	8800	
Modulus of elasticity (Gpa)	173	
Mean coefficient of thermal expansion	0-100°C (µm/m/°C)	13.9
	0-350°C (µm/m/°C)	14.6
	0-538°C (µm/m/°C)	15.3
Thermal conductivity	at 100°C (W/m.K)	21.8
	at 500°C (W/m.K)	26.2
Specific Heat 0-100°C (J/kg.K)	427	
Electrical resistivity (nΩ.m)	547	
Melting point (°C)	1350	

MARKET SECTORS



Food & Beverage Industry

Food handling machinery, storage tanks, processing vessels



Chemical Processing

Tanks, pumps, valves, reactors, vessels, heat exchangers



Marine Equipment

Heat exchangers, condensers, fixtures, fasteners



Electrical Industry

Electrical components, springs, connectors



Oil & Gas Industry

Components for downhole and surface applications



Aerospace Industry

Aircraft components, missile systems, aircraft fuel tanks